

Ethylene - Propylene Rubber (EPR)

Grades	Propylene content %	Mooney viscosity ML(1+4) 125°C	Oil content %	Physical form(2)	Unsaturation level	Main applications
Copolymers						
Dutral CO 034	28	44 (1)	-	B, PL	-	Cables, appliances, polymer modification, V.I.I.
Dutral CO 038	28	60	-	B, FB, FF, PL	-	Automotive, cables, appliances, polymer modification, V.I.I.
Dutral CO 043	45	34 (1)	-	B	-	Automotive, cables, appliances, polymer modification, V.I.I., bitumen modification
Dutral CO 054	41	44 (1)	-	B	-	Automotive, cables, mechanical goods, building, bitumen modification, polymer modification
Dutral CO 058	50	80 (1)	-	B	-	Appliances polymer modification, V.I.I.
Dutral CO 059	41	79	-	B	-	Polymer modification
Dutral CO 555	44	31	48	B	-	Automotive, cables, mechanical goods, building, polymer modification

Grades	Propylene content %	Mooney viscosity ML(1+4) 125°C	Oil content %	Physical form (2)	Unsaturation level	Main applications
Terpolymers*						
Dutral TER 4028	25	60	-	FB, FF, PL	Medium	Automotive, cables, mechanical goods, building
Dutral TER 4033	25	30 (1)	-	FB, PL	Medium	Automotive, cables, polymer modification
Dutral TER 4038 EP	27	60	-	EP, FB, FF, PL	Medium	Automotive, cables, mechanical goods, building, appliances
Dutral TER 4044	35	44(1)	-	B	Medium	Automotive, cables, mechanical goods, building
Dutral TER 4047	40	55	-	B	Medium	Automotive, mechanical goods, building
Dutral TER 4049	40	76	-	B	Medium	
Dutral TER 4334	27	28	30	B	Medium	Automotive, mechanical goods, cables, building, appliances
Dutral TER 4436	28	43	40	B	Medium	Automotive, appliances
Dutral TER 4535	32	32	50	B	Medium	Automotive, mechanical goods, building, appliances
Dutral TER 6148	40	65	15	B	High	Automotive, mechanical goods, building, appliances
Dutral TER 6235	32	33	23	B	High	Automotive, building, appliances
Dutral TER 6537	32	43	50	B	High	
Dutral TER 9046	31	67 (1)	-	B	Very High	

MFI

Pellet/size

Grades	(230°C-5Kg) g/10 mins	Ash wt. max %	Volatiles wt. max %	Physical form (2)	g/30 pellets	Main applications
Polyolefin Modifiers						
Dutral PM 06 PLE	1.8	0.3	0.2	PL	0.45	
Dutral PM 8273	2.4	0.3	0.2	PL	0.45	
Dutral PM 8276	7	0.3	0.2	PL	0.45	
Grade	Propylene content %	MFI (230°C-5Kg) g/10 mins	Ash wt. max %	Volatiles wt. max %	Physical form (2)	Main applications
Oil Modifiers						
Dutral OCP 2530 PL	8.5	0.4	0.2	PL (*)	34	Oil viscosity modifier

(1) ML (1+4) 100°C

(2) B= bales; EP= friable easy processing bales; FF= free flowing crumbs; PL= pellets; FB= friable bales;
PL (*) = NON-FREE FLOWING PELLETS

Storage conditions: store in vented, dry area at temperatures between 20°C and 30°C; no direct sunlight.
Please consult the relevant safety data sheet for more detailed information.